

# CONTOUR COLLECTION

Maplex C is highly formable, medium-density board with moderate dimensional stability. It is ideal for making contoured shapes. This product has a softer appearance than other Maplex grades. Made of 100% cellulose fibers and water.

## **KEY PROPERTIES**

- High-quality fibers deliver combination of mechanical strength and flexibility
- Highly shapeable pressboard maintaining the integrity of the outer and inner curve
- Minimal risk of breaking, wrinkling, creping, or fiber separation
- Recyclable

#### FEATURES AND BENEFITS

- Zero VOC pressboard
- Calendered low-density, highly formable 100% biobased pressboard
- Produced with unbleached softwood cellulose and water
- Light natural kraft color



## **APPLICATIONS**

- Suitable for applications that require tightly curved and/ or rounded shapes
- · Interior decorative paneling
- Clothing hangers
- · Collapsible recyclable storage bins

### TECHNICAL DATA

|                                  |     |            |       | MAPLEX C       |
|----------------------------------|-----|------------|-------|----------------|
| Properties                       |     | Standard   | UOM   | Typical Values |
| Thicknesses range                |     | -          | mm    | >1.3 – 2.3     |
| Apparent density                 |     | ISO 534    | g/cm³ | 1.05           |
| Moisture                         |     | ISO 287    | %     | 4.9            |
| Tensile strength                 | MD  | ISO 1924-2 | MPa   | 82.5           |
| Tensile strength                 | CMD | ISO 1924-2 | MPa   | 48.2           |
| Tensile elongation               | MD  | ISO 1924-2 | %     | 10             |
| Tensile elongation               | CMD | ISO 1924-2 | %     | 13             |
| Modulus of elasticity in tension | MD  | ISO 1924-2 | GPa   | 2.4            |
| Modulus of elasticity in tension | CMD | ISO 1924-2 | GPa   | 1.4            |

The Technical Data reported here are typical results for routine tests made in the Weidmann Laboratory. If not specified, the values are typical for 3mm material. Additional specific data is available on request.

MD - Machine Direction / CMD - Cross Machine Direction.

Maplex custom thicknesses can be manufactured in any dimension ranging from 1.00mm to 8.00mm. Please contact Customer Services for more information.

This matrix is provided for reference purposes only to consider options for your application. While we recommend certain grades that successfully performed in specific applications, our Engineering team will be happy to work closely with you to review your application requirements and select the grade, prototype if necessary, and develop a solution that works best for you.

Some grades can be used and interchanged across multiple applications successfully, our fiber alignment, sheet forming, and fabrication techniques vary for different grades, which provides us with opportunity to find the Maplex grade most suitable for your project.

Made in USA

